

Timken 59188/59412 tapered roller bearings

170 Million used Timken 59188/59412 tapered roller bearings instantly searchable. Shop our 130x95x18 Size (mm) large selection of parts based on brand, price, description, and location. Order the with stock ...

Size (mm)	130x95x18
Bore Diameter (mm)	130
Outer Diameter (mm)	95
Width (mm)	18
d	95 mm
D	130 mm
B	18 mm
d1	107.94 mm
d2	106.36 mm
D2	120.7 mm
r1,2 – min.	1.1 mm
r3,4 – min.	0.6 mm
a	28.2 mm
da – min.	101 mm
db – min.	101 mm
Da – max.	124 mm
Db – max.	126.8 mm
ra – max.	1 mm
rb – max.	0.6 mm
dn	109 mm
Basic dynamic load rating – C	18.2 kN

Basic static load rating – C0	18.6 kN
Fatigue load limit – Pu	0.75 kN
Limiting speed for grease lubrication	16000 r/min
Limiting speed for oil lubrication	24000 mm/min
Ball – Dw	7.144 mm
Ball – z	38
Gref	7.5 cm ³
Calculation factor – f0	10
Preload class A – GA	60 N
Preload class B – GB	120 N
Preload class C – GC	360 N
Calculation factor – f	1
Calculation factor – f2A	1
Calculation factor – f2B	1.03
Calculation factor – f2C	1.08
Calculation factor – fHC	1.01
Preload class A	62 N/micron
Preload class B	82 N/micron
Preload class C	130 N/micron
r1,2 min.	1.1 mm
r3,4 min.	0.6 mm
da min.	101 mm
db min.	101 mm
Da max.	124 mm
Db max.	126.8 mm
ra max.	1 mm
rb max.	0.6 mm
Basic dynamic load rating C	24.7 kN
Basic static load rating C0	30 kN

Fatigue load limit P_u	0.75 kN
Attainable speed for grease lubrication	16000 r/min
Attainable speed for oil-air lubrication	24000 r/min
Ball diameter D_w	7.144 mm
Number of balls z	38
Reference grease quantity G_{ref}	7.5 cm ³
Preload class A G_A	60 N
Static axial stiffness, preload class A	62 N/ μ m
Preload class B G_B	120 N
Static axial stiffness, preload class B	82 N/ μ m
Preload class C G_C	360 N
Static axial stiffness, preload class C	130 N/ μ m
Calculation factor f	1.13
Calculation factor f_1	1
Calculation factor f_{2A}	1
Calculation factor f_{2B}	1.03
Calculation factor f_{2C}	1.08
Calculation factor f_{HC}	1.01
Calculation factor f_0	10
Mass bearing	0.58 kg